SD-0150 GENERAL PURPOSE ABS (Acrylonitrile – Butadiene – Styrene)

1) Product Description:

panizapolymer.com General Purpose ABS, SD – 0150 grade, is a rigid thermoplastic with good processing characteristics. It is a high flow injection molding grade with considerable impact strength and medium heat deflection.

2) Applications:

apolymer.com This grade is intended for a wide range of applications including auto parts, home appliances, electrical parts/fittings, telecommunication and electronic devices.

3) Typical Data

	telecommunication and electronic devices. 3) Typical Data		:zapolymer.com		
	PROPERTY	TEST METHOD	TEST CONDITION	UNIT	TYPICAL VALUE
	MFI	ASTM D 1238	(200°c/5kg)	Gr/10 min	1.7
	Izod Impact Strength (notched)	ISO 180	1/8 inch	Kj / m2	25
	Tensile Strength @ Yield	ASTM D 638	5mm/min	Kgf/cm2	440
	Elongation @ Break	ASTM D 638	5mm/min	%	40
	Flexural Strength @ Yield	ASTM D 790	2.8mm/min	Kgf/cm2	640
	Flexural Modulus	ASTM D 790	2.8mm/min	Kgf/cm2	20500
	Vicat Softening Temperature (unannealed)	ASTM D 1525	5kg	°C	99
	Rockwell Hardness	ASTM D 785		R-Scale	104
	Flammability	UL 94	1.5mm Specimen	Recognized	HB

^{*}Typical Values : not to be construed as specifications Density of this grade is approximately 1.04 gr/cm $^{'}$. Shrinkage of all ABS grades in mold is approximately 0.3 % \sim 0.6 % (ASTM D 955). All tests are carried out at 23 °C unless otherwise stated. The above data are typical laboratory average. They are intended to serve as guide only.

4) Processing Condition: SD-0150 ABS granules absorbs moisture from atmosphere, with a rate depending on temperature and humidity. It is recommended that the material be dried in a dehumidifying dryer at 80 °C to 85 °C for 2-4 hours, prior to use. Avoid excessive melt temperatures and long residence time, as they may cause thermal degradation. Processing temperatures are recommended to be set at 190 °C - 230 °C for cylinder, and 40 °C - 80 °C for mold. SD-0150 ABS can be processed under different conditions based on machinery available and articles molded.

Producer: Tabriz Petrochemical Co. panizapolymer.com

Licensor: SAMUNG Packing: 25 Kg plastic bag panizapolym